

**Technical Data Sheet**

<b>PUR-TRA C.15 VD</b>	<b>SERIE 500</b>	<b>Cod. DS 5XX</b>
------------------------	------------------	--------------------

Powder Coatings: TGIC FREE POLYURETHANE

Use: Outdoor

Suggested for: Base coat for heat transfer process

Application: Corona Charging

Curing Cycle: 20' X 200°C ( Metal Temperature )

**Chemical and Mechanical Properties**

1 - Packing: 20 Kg. Boxes with PE-bag, palletized and shrink-wrapped

2- Shelf-life: In a dry place with a temperature lower than 35 °C  
for 6 months

3 - Specific weight: 1.25 ± 0.05 g/cm<sup>3</sup>

4 – Yield m<sup>2</sup>/Kg. considering 60 microns film thickness: 13 m<sup>2</sup>/Kg

60 microns film thickness

5 - Appearance: Semimatt

	<b>RIF Standard</b>	<b>Miniumum Tollerance Limit</b>	<b>Result</b>
6 - Gloss ( Gardner 60°)	ISO 2813	20 ± 5 gloss	OK
7 - Buchholz hardness	ISO 2815	minimum 80	OK
8 - Adhesion	ISO 2409	No loss of Adhesion	OK
9 - Thickness ( Minim. thickness)	ISO 2360	60 microns	OK
10 - Direct Impact Test *	ASTM D2794	2,5 N/m	No Coating detaching
11 - Reverse Impact Test	ASTM D2794	2,5 N/m	No Coating detaching
12 - Erichsen Identation *	ISO 1520	5 mm	No Coating detaching
13 - Bending *	ISO 1519	5 mm diameter	No Coating detaching
14 - Kesternich Test	ISO 3231	No Coating detaching or penetration higher than 1 mm.	OK
15 - Humidity Test**	DIN 50017	No blistering/coating detaching	OK
16 - Acetic acid - Salt Spray Test **	ISO 9227	Corrosion lower than 4 mm.	OK
17 - Accellerated weathering Test	ISO 11341	Rit. di Brill. >50% ΔE < 2	OK
18 - Pressure Cooker Test	Cap.Qualicoat	No blistering/coating detaching	OK
19 - Lime Resistance	Cap.Qualicoat	No blistering/coating detaching	OK

\* Tests carried out on 1 mm. thickness alloy AA5005 H24 chromate aluminium sheets and 60 microns coating layer .

\*\* Tests carried out on AA6060 extruded alloy

This technical information is reliable to the best of our and our customers' experience but non warranty or guarantee is implied.

Users will assume responsibility for the application of the product testing its characteristics on their own equipment and carriers.